## Pyrite (FeS<sub>2</sub>) oxidation as a function of pH: a multitechnique approach

M. DESCOSTES<sup>1,2</sup>, C. BEAUCAIRE<sup>1</sup> AND P. VITORGE<sup>1,2</sup>

This work intents to identify the  $FeS_2$  oxidation mechanism and to evaluate the effects of carbonates during its dissolution. Oxidative dissolution experiments are carried out at several pH associating solution speciation to surface solid analysis (XPS, FTIR, SEM and Nuclear Microprobe Analysis). The influence of carbonates is investigated at several contents in equilibrium with air.

We show that fast FeS<sub>2</sub> air oxidation explains the disparity of both results and oxidation mechanisms published.

Previous works indicate S at oxidation number 0 (FeSSO) and 2 (FeS $_2$ O $_3$ ) on localized points of FeS $_2$  surface (Descostes *et al.*, 2001). SO $_4$ <sup>2-</sup> and S $_2$ O $_3$ <sup>2-</sup> are the main S aqueous species whatever the pH. Under acidic conditions (pH<3) a S deficit leads to ratios R=[S]<sub>tot</sub>/[Fe]<sub>tot</sub><2 (Descostes *et al.*, 2004). Given a kinetic model FeS $_2$  dissolution may be ruled by a localized first solid-state oxidation step followed by S $_2$ O $_3$ <sup>2-</sup> dissolution. In acidic media S $_2$ O $_3$ <sup>2-</sup> dismutation into S $_0$  and S $_4$ O $_6$ <sup>2-</sup> explains the observed uncongruence with a predicted S/Fe ratio: R=1.6. This work offers a new sight of the well accepted iron preferential dissolution models.

In buffering conditions  $\Sigma CO_2 \ge 10^{-2}$  mol/L 90% of aqueous S is under  $S_2O_3^{-2}$  form. The dissolution rate raises with  $\Sigma CO_2$ . The observed  $FeS_2 \rightarrow$  siderite  $FeCO_3 \rightarrow$  goethite  $\alpha$ -FeOOH  $\rightarrow$  lepidocrocite  $\gamma$ -FeOOH  $\rightarrow$  ferric sulfate transformation can't be predicted by an equilibrium thermodynamic model. The competition between Fe(II) oxidation and complexation - precipitation explains the raising of the dissolution rate vs  $\Sigma CO_2$ . Concurrently a component GR-SO $_3$  from the green rust compounds family incorporates  $SO_3^{-2}$ .

## References

Descostes M., Mercier F., Beaucaire C., Zuddas P. and Trocellier P, (2001), *Nucl. Instr. and Meth. B*, **181**, 603-609.

Descostes M., Beaucaire C. and Vitorge P. (2004), Geochimica et Cosmochimica Acta, 68, 4559-4569

<sup>&</sup>lt;sup>1</sup> CEA Saclay DEN/DPC/SECR, 91191 Gif sur Yvette Cedex (France), michael.descostes@cea.fr

<sup>&</sup>lt;sup>2</sup> UMR 8587 CEA – Université d'Evry – CNRS (France)